



CRUSHED ROCK REQUIRED GRADATION	
100% passing	1"
90-100% passing	3/4"
20-55% passing	3/8"
0-10% passing	#4
0-5% passing	#8

**NOTE:**  
 Refer to Specifications for pipe bedding requirements in rock or unstable ground.  
 SEWER: 3/4 CRUSH ROCK  
 WATER: IMPORT SAND



APPROVED DATE: January 1, 2011

*Joseph Brandy*

\_\_\_\_\_  
 DIRECTOR OF ENGINEERING

STANDARD DRAWING  
 CLASSES "BB", "B", "C"  
 & "D" BEDDINGS

STD. DWG. NO.  
 W-1030